CLAIMS

A solid catalyst component for the polymerization of olefins CH₂=CHR, in which R is 1. hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, comprising Mg, Ti, halogen and an electron donor selected from succinates of formula (I):

$$\begin{array}{c|c}
R_3 & \parallel \\
R_4 & C & O \\
R_5 & \parallel & O \\
R_6 & \parallel & O
\end{array}$$
(I)

wherein the radicals R₁ and R₂, equal to or different from each other, are a C₁-C₂₀ linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, optionally containing heteroatoms; the radicals R₃ to R₆ equal to or different from each other, are hydrogen or a C_1 - C_{20} linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, optionally containing heteroatoms, and the radicals R₃ to R₆ which are joined to the same carbon atom can be linked together to form a cycle; with the proviso that when R₃ to R₅ are contemporaneously hydrogen R6 is a radical selected from primary branched, secondary or tertiary alkyl groups, cycloalkyl, aryl, arylalkyl or alkylaryl groups having from 3 to 20 carbon atoms.

- Catalyst component according to claim 1 in which the electron donor compound of formula 2. (I) is selected from those in which R_1 and R_2 are C_1 - C_8 alkyl, cycloalkyl, aryl, arylalkyl and alkylaryl groups.
- Catalyst components according to claim 2 in which R₁ and R₂ are selected from primary 3. alkyls.
- Catalyst component according to claim 1 in which the electron donor compound of 4. formula (I) is selected from those in which R_3 to R_5 are hydrogen and R_6 is a branched alkyl, cycloalkyl, aryl, arylalkyl and alkylaryl radical having from 3 to 10 carbon atoms.
- The catalyst component according to claim 4 in which R_6 is a branched primary alkyl group or Catalyst component according to claim 4 in which R_6 is a branched primary alkyl group or 5.

a cycloalkyl group having from 3 to 10 carbon atoms.

- 6. Catalyst component according to claim 1 in which the electron donor compound of formula (I) is selected from those in which at least two radicals from R₃ to R₆ are different from hydrogen and are selected from C₁-C₂₀ linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl groups optionally containing heteroatoms.
- 7. Catalyst component according to claim 6 in which the two radicals different from hydrogen are linked to the same carbon atom.
- 8. States component according to claim 6 in which the two radicals different from hydrogen are linked to different carbon atoms.
- Catalyst component according to claim 8 in which the succinate of formula (I) is selected 9. from diethyl 2,3-diisopropylsuccinate, diisobutyl 2,3-diisopropylsuccinate, di-n-butyl 2,3-2,3-dicyclohexyl-2-methylsuccinate, 2,3diethyl diisopropylsuccinate, 2,2diethyl 2,2-dimethylsuccinate, dicyclohexyl-2-methylsuccinate, diisobutyl 2-ethyl-2diisobutyl 2-ethyl-2-methylsuccinate, diethyl dimethylsuccinate, methylsuccinate, diethyl 2-(cyclohexylmethyl)-3-ethyl-3-methylsuccinate, diisobutyl 2-(cyclohexylmethyl)-3-ethyl-3-methylsuccinate.
 - 10. A solid catalyst component according to any of the preceding elaims in which the succinates are used in the form of pure stereoisomers.
 - A solid catalyst component according to any of the preceding claims in which the succinates are used in the form of mixtures of enantiomers, or mixture of diastereoisomers and enantiomers.
 - 12. A solid catalyst component according to claim in which diethyl 2,3-diisopropylsuccinate, diisobutyl 2,3-diisopropylsuccinate and di-n-butyl 2,3-diisopropylsuccinate are used as a pure rac or meso forms, or as mixtures thereof.
 - 13. A solid catalyst component according to any of the preceding claims comprising a titanium compound having at least a Ti-halogen bond and the succinate of formula (I) supported on a Mg dichloride in active form.
 - P 14. A solid catalyst component according to claim 10 in which the titanium compound is TiCl₄ or TiCl₃.
 - A solid catalyst component according to any of the preceding comprising another electron

m

T

20.

donor compound in addition to the succinate of formula (I).

- 16. A solid catalyst component according to claim 15 in which the additional electron donor compound is selected from ethers, esters of organic mono or bicarboxylic acids and amines.
- 17. A solid catalyst component according to claim 16 in which the additional electron donor compound is selected from the mono or bicarboxylic acids.
- 18. A solid catalyst component according to claim 17 in which the additional electron donor compound is selected from phthalates or the 1,3-diethers in which R^{VII} and R^{VIII} are selected from C₁-C₄ alkyl radicals, R^{III} and R^{IV} form a condensed unsaturated cycle and R^I, R^{II}, R^V and R^{VI} are hydrogen.
- A catalyst for the polymerization of olefins CH₂=CHR, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, comprising the product of the reaction between:
 - the solid catalyst component of any of the claims 1-18;
 - an alkylaluminum compound and, optionally,
 - one or more electron donor compounds (external donor).

 The catalyst
 Catalyst according to claim 19 in which the alkylaluminum compound (b) is a trialkyl
 - aluminum compound.

 Catalyst according to claim 20 in which the trialkylaluminum compound is selected from triethylaluminum, triisobutylaluminum, tri-n-butylaluminum, tri-n-hexylaluminum, tri-n-hexy
- octylaluminum.

 22. Catalyst according to claim 19 in which the external donor (c) is selected from the 1,3-diethers of the general formula (II):

$$R^{II} \longrightarrow QR^{VIII}$$

$$R^{IV} \longrightarrow QR^{VII}$$

$$R^{VI} \longrightarrow R^{VI}$$

$$(II)$$

1 26.

27.

A [28.

wherein R^I, R^{II}, R^{III}, R^{IV}, R^V and R^{VI} are equal or different to each other, hydrogen or hydrocarbon radicals having from 1 to 18 carbon atoms, and R^{VIII} and R^{VIII}, equal or different from each other, have the same meaning of RI-RVI except that they cannot be hydrogen; one or more of the RI-RVIII groups can be linked to form a cycle.

The Catalyst according to claim 22 in which the 1,3-diethers are selected from those in which R^{VII} and R^{VIII} are selected from C_1 - C_4 alkyl fadicals, R^{III} and R^{IV} form a condensed 23. A unsaturated cycle and R^{I} , R^{II} , R^{V} and R^{VI} are hydrogen.

The country according to claim 23 in which the diether of formula (II) is 9,9-24. P bis(methoxymethyl)fluorene.

Catalyst according to claim 19 in which the external donor (c) is a silicon compound of formula R_a⁷R_b⁸Si(OR⁹)_c, where a and b are integer from 0 to 2, c is an integer from 1 to 4 25. and the sum (a+b+c) is 4; R⁷, R⁸ and R⁹ are C1-C18 hydrocarbon groups optionally (n containing heteroatoms. ïŲ ij

The cataint Catalyst according to claim 25 in which a is 1, b is 1 and c is 2.

Catalyst according to claim 25 or 26 in which R7 and/or R8 are branched alkyl, cycloalkyl or aryl groups with 3-10 carbon atoms optionally containing heteroatoms and R^9 is a C_1 - C_{10} alkyl group, in particular methyl.

The catalyst according to claim 25 in which a is 0, c is 3 and R⁸ is a branched alkyl or cycloalkyl group and R9 is methyl.

A catalyst for the polymerization of olefins CH₂=CHR, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, comprising the product of the reaction (PA duz between:

- (i) a solid catalyst component comprising Mg, Ti, halogen and an electron donor (d);
- (ii) an alkylaluminum compound and,
- (iii) a succinate of formula (I).

The calcust according to claim 29 in which the succinate of formula (I) is selected from those 30. in which at least two radicals from R₃ to R₆ are different from hydrogen and are selected A from C_1 - C_{20} linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl groups optionally containing heteroatoms.

Catalyst component according to claim 30 in which the two radicals different from *



hydrogen are linked to different carbon atoms.

The catalant

Catalyst according to claim 29 in which the internal donor (d) is selected from ethers, esters

of organic mono or bicarboxylic acids and amines.

Catalyst according to claim 32 in which the internal donor (d) is selected from the 1,3
SUL A10) propanediethers of formula (II) and esters of organic mono or bicarboxylic acids.

- 34. Catalyst according to claim 33 in which the internal donor (d) is selected from phthalates or the 1,3-diethers in which R^{VII} and R^{VIII} are selected from C₁-C₄ alkyl radicals, R^{III} and R^{IV} form a condensed unsaturated cycle and R¹, R¹, R^V and R^{VI} are hydrogen.
- 35. A prepolymerized catalyst component for the polymerization of olefins CH₂=CHR, wherein R is hydrogen or a C₁-C₁₂ alkyl group, characterized by comprising a solid catalyst component according to claim 1 10 which has been prepolymerized with an olefin to such an extent that the amount of the olefin pre-polymer is from 0.2 to 500 g per g of solid catalyst component.

The prepalymented atalyst according to claim 35 in which the solid catalyst component has been prepolymerized with ethylene or propylene.

Process for the (co)polymerization of olefins CH₂=CHR, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, carried out in the presence of any of the catalysts of claims 19-36.

catalysts of claims 19-36.

The process according to claim 37 in which the olefin to be (co)polymerized is selected from he of the control of

39. Propylene polymers characterized in that they have a polydispersity index of higher than 5, a content of isotactic units expressed in terms of pentads of higher than 97% and a flexural modulus of at least 2000 MFa.

Propylene polymers according to claim 39 in which the polydispersity index is higher than 5.1, the flexural modulus is higher than 2100 and the percent of propylene units in form of pentads is higher than 97.5%.

ADD A13>

[∏] 36.

DE BYSKIN 3: